



# UNIWALL CONCENTRATE

Fiber-Reinforced Stucco System



## Coverage

Approximately 8yd to 10yd per bag at 3/8" thick. Coverage may vary depending on the amount of sand and water used, along with various depth of lath. Surface porosity mixing and application methods can contribute to various yields.

## Packaging

Multi-layered, moisture resistant, 80 lb. bags.

## Storage

1. Protect bags from weather and other damage
2. Store bags in a cool, dry location
3. Store out of direct sunlight
4. Store away from direct contact with the ground and/or concrete

## Shelf Life

1 Year

## Color

Natural Grey



SCAN FOR  
FULL LIST  
OF SPEC SHEETS



## Product Description

Superior Stucco Uniwall fiber-reinforced stucco system is a proprietary mixture of Portland cement, sand, fibers, water and proprietary ingredients reinforced with wire fabric or metal lath and applied to substrates of expanded polystyrene (EPS) insulation board, gypsum sheathing, fiberboard or plywood.

## Features

## Benefits

Durable	Superior weathering properties
Fiber-Reinforced	Reduced cracking when cured properly
Single application with some finish coats able to be applied within 24 hours	Reduced labor and scaffolding costs; schedule savings
1-Hour Fires-Resistant-Rated	Single-family, multi-family, and commercial applications

May be used in the exterior design and construction of exterior wall assemblies in new building in a Fire Hazard Severity Zone within the State Responsibility Areas or any Wildland-Urban Interface Area. CA SFM Ch 12-7A-1 Listing Service : 8140-2395:0001

## Basic Uses

Uniwall is designed for use as a base coat in residential and commercial wall assemblies. Uniwall provides an ideal base coat for the application of Superior Stucco Color Coat or Superior Stucco Acrylic Finish. Uniwall concentrate exceeds ASTM C926 requirements for scratch and brown coats and may be used in three-coat stucco applications. For one coat stucco systems refer to ICC - ESR - 5231 Report

## Area of Use

Uniwall concentrate may be applied over the following substrates:

1. Wood or OSB
2. Exterior grade gypsum sheathing/glass mat reinforced gypsum sheathing
3. Fiber board
4. EPS, XPS, or polyisocyanurate foam boards
5. Masonry
6. Poured-in-place and/or tilt-up concrete
7. Other approved cementitious boards
8. Lath (three coat application only)

## Optional Product Upgrades/Enhancements

Product	Benefit
Admix 2000, Ultra-Tite 60, Acrylic Bonder	Liquid admixtures that reduce cracking and increase tensile, bond, and flexural strengths.
Crack Guard System	Supplementary system designed to mitigate surface cracking in new and existing plaster systems by integrating woven fiber glass mesh into the base coat or brown coat, prior to applying the finish.
Uniwall PM	Premium one-coat stucco system with improved crack resistance, flexural and tensile strength, and impact resistance.

# Application Instructions

## Surface Preparation

### Solid Substrates

For solid substrates, such as concrete or masonry, surfaces to receive application must be structurally sound, clean and free of debris, dirt, dust, efflorescence, grease, oils, curing agents and cleaning solutions. Repair cracks with the appropriate patching material for the existing substrate as needed. Bonders or admixtures may be required to insure proper adhesion.

### Framing

Ensure substrates, water-resistive barrier, and lathing have been installed and inspected as required by ICC-ESR-5231 report, Superior Stucco Product's literature and/or local building codes as applicable.

## Mixing

1. Add approximately four to six gallons of potable water per bag, to mixing apparatus.
2. Add Uniwall concentrate and optional admix per admix data sheet.
3. Add 160lb to 240lb of plaster sand, meeting ASTM C144 and/or ASTM C897. Amount of sand added may vary due to moisture content and/or composition of plaster sand.
4. Mix for approximately 3 to 5 minutes.
5. Stop mixer and allow the material to take its initial set.
6. Material may be retempered once adding only enough water to reach the desired consistency.

Note: Do not over mix.

## Application

Uniwall can be hand troweled or machine applied.

1. Apply the mixed Uniwall per ICC-ESR-5231 for one coat application or ASTM C926 for three coat application.
2. Rod or screed to achieve a uniform surface.
3. Float the freshly applied Uniwall to ensure even suction.

## Curing

Provide sufficient moisture by fog or moist curing to permit proper hydration of the Uniwall. The length of time and most effective procedure for curing will depend on climatic and job conditions. Product should fully cure in 7 to 28 days following application. Curing time may vary due to ambient temperature, surface temperature, surface porosity, application methods, and/or thickness of material. All freshly applied material must be protected by an approved protective system from inclement weather until cured. It is the responsibility of the applicator to determine if the product is cured and/or dry prior to exposing it to rain, snow, dew, and/or any other inclement weather condition that may be detrimental to the product.

## Limitations

DO NOT apply product when the ambient and surface temperature is below 40°F (4°C). When hot, dry, or windy conditions exist, moist curing and protection must be provided. The ambient and surface temperature must maintain the above requirements until fully cured (See CURING). Material that is allowed to freeze may suffer irreparable damage. Protect all work from inclement weather with an approved protective system until fully cured.

DO NOT add any other materials to the mixture of the product without written approval from Superior Stucco.

DO NOT deviate in the mixing or application procedures contained in this, or any other Product Data Sheets, without written approval from Superior Stucco.

DO NOT apply Uniwall if there are contaminants on the receiving surface. Contaminates may include, but are not limited to, dust, debris, efflorescence, and/or oils.

DO NOT add any more water than prescribed.

DO NOT saturate the wall during preparation and/or water curing.

DO NOT use excessive amounts of water when floating.

Note: Failure to manufacturer's written specifications could result in the following, but not limited to spalling, cracking, peeling, chipping, delamination, discoloration, wash off, and overall system failure.

## Cleaning

Cleaning may be accomplished with water immediately after use.

## Safety

Avoid contact with eyes or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush immediately with running water for at least 15 minutes. Consult a physician immediately. Do not take internally. Be sure to adequate ventilation in enclosed areas. Use of an approved respirator is recommended.

KEEP OUT OF REACH OF CHILDREN

Scan to access ICC Report



ICC-ESR-5231

www.StuccoSupplyCo.com

### DISCLAIMER

Superior Stucco (Manufacturer) MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT(S) SOLD HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer and are given for informational purposes ONLY and without any responsibility for their use. It is expressly understood that the buyer's sole and exclusive remedy for any claimed defective product against Manufacturer shall be the replacement of products actually proven to be defective. Handling and use of products are beyond the control of Manufacturer, therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product. Under no circumstance shall Manufacturer be liable for incidental or consequential damages arising out of the use or the improper application of the product. Before applying the product, the user shall determine the suitability of the product for his/her independent use, assuming all risks and liability whatsoever in connection therewith. This writing constitutes a complete and exclusive statement of the understanding between Manufacturer and Buyer.

### CLAIMS

Any Claimant shall notify Manufacturer immediately in writing of any alleged defect in the material. Claimant will provide Manufacturer with a reasonable and exclusive opportunity to investigate and test for alleged defect. For any claim that is not valid Claimant agrees to pay Superior Stucco's reasonable charges, including travel and labor associated with investigation of such claim.

### TECHNICAL ASSISTANCE

Technical assistance and information is available by calling Stucco Supply at (408) 292-0454

### WARRANTY

The following is made in lieu of all expressed and implied rights, warranties and conditions, statutory or otherwise. The manufacturer's only obligation shall be to replace such quantity of products proven to be defective within 1 year following the date of manufacturer, provided that the alleged defective product is returned to the manufacturer's plant and is accompanied with proof of purchase and batch number.